

PC Technical Data Sheet(TDS)

Physical Properties	Methods	Value
Density	ISO 1183, GB/T1033	1.19 g/cm ³ at 21°C
Melt Index	260°C, 1.2Kg	6-8 g/10 min
Flame Retardancy V2	UL94	V2

Mechanical Properties	Methods	Value
Glass transition	DSC, 10°C/min	113°C
Decomposition Temperature	TGA, 20°C/min	>360°C
Vicat softening Temperature	ISO 306 GB/T 1633	116.9°C
Heat deflection Temperature	ISO 75 108 MPa	99.3°C
Heat deflection Temperature	ISO 75 0.45MPa	114.1°C

Property	Testing Method	Typical Value
Young's modulus (X-Y)	ISO 527, GB/T 1040	2048 \pm 66MPA
Young's modulus (Z)		1845 \pm 35 MPA
Tensile Strength (X-Y)	ISO 527, GB/T 1040	59.7 \pm 1.8 MPA
Tensile Strength (Z)		29.1 \pm 4.1 MPA
Elongation at break (X-Y)	ISO 527, GB/T 1040	12.24 \pm 1.44 %
Elongation at break (Z)		1.84 \pm 0.14 %
Bending modulus (X-Y)	ISO 178, GB/T 9341	2044 \pm 58 MPA
Bending modulus (Z)		N/A
Bending Strength (X-Y)	ISO 178, GB/T 9341	94.1 \pm 0.9 MPA
Bending Strength (Z)		N/A
Charpy impact strength (X-Y)	ISO 178, GB/T 9341	25.1 \pm 1.9kJ/m ²
Charpy impact strength (Z)		N/A

Updated on November 11, 2022